



WEIGHT (approximate weight per square foot)

C Series	9 lbs
E Series	8 lbs
F Series	9 lbs
N Series	12 lbs
SQ Series	9 lbs
CPM Series	8 lbs
IPM Series	8 lbs

THICKNESS (approximate thickness)

C Series	1"
E Series	3/4"
F Series	1"
N Series	1 1/2"
SQ Series	1 1/4"
CPM Series	3/4"
IPM Series	3/4"

COLOUR RANGE

All Millennium Feature Stone products are produced from natural stone. Due to the nature of natural stone, colour may vary between batches. This is standard across the natural stone industry.

Code Colour and stone type

03	Kakadu Green Limestone
14	Sydney Yellow Quartzite
18	Springwood Black Slate
24	Outback Brown Slate
40	Cream Quartzite

INSTALLATION

Please review full installation instructions prior to installation.

Adhesive

Exterior applications: a flexible latex based mortar system is recommended.
Interior applications: a thin set mortar suitable for stone is recommended.
For light colored stones, a white mortar is recommended.

Substrates

Exterior and interior:
Fully cured concrete (at least 28 days cured)
Masonry brick
Regular brick
Cement mortars
Cementitious backer units

Interior Only:
Gypsum plaster (max 10' high)
Gypsum wallboard (max 10' high)
Exterior grade plywood (max 10' high)
Cementitious backer units

FREEZE – THAW (ASTM C-97)

Average water absorption of stone – 0.1%
Average mass loss through freezing – Nil
No changes to stone during and after the frost – thaw cycles.

RESISTANCE TO SALT ATTACK

Average mass loss after 15 cycles – Nil

COMPRESSIVE STRENGTH

Average compressive strength – 60.3 MPa